

DATA SHEET

NEOPRENE

ANR-451

Color:		Black
Specifications:	ASTM D-1056-00	2C5
	ASTM D-1056-67(1)	SCE45
	SAE J18-02	2C5
	GM 6086M(3)	IIIA
	GMN11106(3)	IIIA
	TSM1501G	2C5
25% Compression Deflection (PSI)		16 - 24
Shore 00 Durometer (Approximate)		65+
Density (Approximate p.c.f.)		21 - 35
Water Absorption By Weight		5%
Temperature Range		-40 to 200F
Weather Resistance:	UV	Excellent
	Ozone	Fair
Accelerated Linear Shrinkage (Typical)		5%
Fuel B Resistance %		150
Tensile Strength (Typical)		150 PSI
Elongation (Typical)		140%
Flammability:	FM VSS No. 302	Pass
	ASTM D 6576	Pass

(1)Obsolete specification listed for reference only. ANR certifies to most recent revision of ASTM D-1056 and SAE J18.

(3)Certain sections of this specification will not apply to all products. Contact Customer Service for details.

American National Rubber disclaims responsibility for results of use of this information, which is furnished without charge, or of any product mentioned herein. It is the user's responsibility to make and be guided by his own testing before making a final decision on the type of material to be used in any application.

ISO 9001-2000 Certified Company