


F13789 (P03) Black Perfluoroelastomer (FFKM) Product

General Information

- Peroxide cured for the widest chemical resistance (see chart below)
- Excellent heat (to 320°C) resistance and overall thermal stability
- Superior mechanical (tensile, elongation, etc.) properties
- Meets/exceeds the AMS7257D aerospace specification (QPL pending)



Applications

- Aerospace: Engines, Auxiliary Power Units (APUs)
- Chemical Processing/Petrol Refining: Mechanical Seals, Flanges, Filters and Valves
- Paint & Coatings: Canisters, Spray Guns
- Semiconductor: Wet stations, Filters, Valves, Lids, Furnace Doors

Material

- Black in Color
- 100% Virgin Materials
- Meets Specification AMS7257D
- Full test specs/lab report available via www.precixinc.com/Perfluoroelastomer.asp

Specifications

Durometer	77
Tensile Strength (psi)	2287
Elongation	173
C-set (70 hrs @ 446F)	30%
TR-10 (low temp)	-1°C

Cure Type Compare

Chemical	Peroxide	Bisphenol	Triazinic
Alkali	Excellent	Good	Poor
Amines	Excellent	Good	Poor
Hot water / Steam	Excellent	Good	Poor
Ketones	Excellent	Excellent	Excellent
Solvents	Excellent	Excellent	Excellent
Esters / Ethers	Excellent	Excellent	Excellent
Acids	Good	Poor	Excellent

Interchange

Kalrez[®] 4079, 6375, 7075
Parker V8545-75
Chemraz[®] 505, 555, 615
Simriz[®] Z7257, 481, SZ485, 487, 498